

Clasificari/Standarde

Autorizari

EN 12536: OI
EN 754-95: S1
AWS A 5.2-80: R 45 mod

DESCRIERE SI APLICATII

Sarma plina cu continut scazut de carbon pentru sudarea oxiacetilenica a otelurilor carbon. Recomandata pentru sudarea tevilor, recipientilor, constructiilor metalice.

PROPRIETATI FIZICE

Punct de topire = 1530 °C.

POZITII DE SUDARE**COMPOZITIA CHIMICA A DEPOZITULUI**

C %	Mn %	Si %	S %	P %	Cu %
0,04 0,10	0,40 0,60	max. 0,15	max. 0,025	max. 0,025	max. 0,025

AMBALARE

DIAMETRU mm	LUNGIME mm	Kg/pachet	Kg/cutie
2,00	300	3,5	14,0
2,50	300	3,0	12,0
2,50	350	4,0	16,0
3,25	350	4,0	16,0
3,25	450	5,0	20,0
4,00	350	4,0	16,0
4,00	450	5,0	20,0
5,00	450	5,0	20,0
6,00	450	5,0	20,0

Datele menționate pot fi modificate fără o notificare prealabilă.